

EZ-FILM™-30

30-MICRON TEXTILE CAPILLARY FILM; PRICED AS A VIABLE ALTERNATIVE TO DIRECT EMULSION; FAST DRYING; FAST EXPOSING PURE PHOTOPOLYMER (SBQ)

EZ-FILM-30 is ideal for standard textile printing--and priced to be an economical alternative to direct emulsion in material cost and because it offers significant savings in labor and production time. We recommend **EZ-FILM-30** for mesh counts ranging from 230 – 419 threads/ inch (90 – 165 threads/cm.). **EZ-FILM-30** is pink in color and coated on 300-gauge matte-surface polyester. **EZ-FILM-30** is sold in prepackaged sheets 15 X 17 inches (≈ 38 X 43 cm.) and 17 X 24 inches (43 X 61 cm.). It adheres perfectly, dries faster than direct emulsion, and exposes quickly. **EZ-FILM-30** can be adhered with plain water or with **QTX®** direct emulsion in the direct/indirect mode.

INSTRUCTIONS

Step 1: PREPARE THE FABRIC

Used or surface-treated fabric need only be degreased using **Screen Degreaser Liquid No. 3** or dilute **Screen Degreaser Concentrate No. 33**, or **Magic Mesh Prep™**. (Mechanical abrasion, an option for new fabric that is not surface treated, increases the surface area of fabric for a better wetting of the fabric, which improves adhesion, and a better mechanical bond of the stencil, which increases printing run length. Use **Microgrit No. 2** before degreasing. Abrading and degreasing can be combined in one step with **Ulanogel 23**.) Rinse thoroughly. Use **Magic Mesh Prep** or **CDF® Mesh Prep No. 25** to promote the water retention if the mesh during the adhering step. (**Magic Mesh Prep** also acts as both a degreaser and an antistatic treatment.)

Step 2: ADHERE EZ-FILM-30 TO THE FABRIC

Standard Method: Position sheet of **EZ-FILM-30** on a flat surface, emulsion side up. Place the printing side of a wet screen (preferably directly following the fabric preparation rinse) on top of the film. The film will darken as it is wetted. Use light pressure to press out to the edge of the film any bubbles or gaps between the film and the mesh, then make a single squeegee stroke across the squeegee side. Wipe off any excess water. "Roll-Down" Method: Roll the film, emulsion side out, around a small-diameter plastic tube (ca. 1" – 1 ½"; 2 ½ X 4 cm.). If the screen fabric is not already wet, soak it from the squeegee side. Contact the edge of the roll to the printing side of the mesh at the top end of the screen. Unwind the roll, maintaining firm contact with the mesh. Make one light squeegee stroke across the squeegee side to remove excess water.

Step 4: DRY THE SCREEN; REMOVE THE BACKING SHEET

Dry the screen thoroughly at room temperature. Use a fan to speed drying. If possible, use a dehumidifier in the drying area. Under humid conditions, dry the screen in a commercial dryer with filtered air < 104° F. (40° C.). Immediately before exposure, remove the backing sheet.

Step 5: CALCULATE THE APPROXIMATE EXPOSURE

From the Base Exposure Table (reverse side), identify the light source you are using. The exposure time shown is your Base Exposure Time. Multiply your Base Exposure Time by all relevant Exposure Variable Factors (reverse) to find your Approximate Exposure Time.

Step 6: DETERMINE THE OPTIMAL EXPOSURE TIME

Make a Step Wedge Test (instructions can be found on the Ulanog Web site: www.ulano.com) or use the **Ulanog Exposure Calculator Kit**—carried through to actual printing—to determine your optimum exposure time. Optimum exposure is indicated: ■ At that exposure time when the film first reaches its maximum color density and the edges of the positive do not "resolve." ■ The squeegee side of the stencil is hard and not soft or slimy. ■ The print best duplicates the test positive *at the level of resolution that the job requires*. (Note that, since resolution is relative to stencil thickness, it is not possible to resolve a line finer than the overall thickness of the fabric and stencil.)

Step 7: WASHOUT:

Wash out the stencil with water *from the printing side only* using high pressure or a power washer. When the image areas start to open, reduce the water pressure and rinse the stencil from the printing side until the image areas are completely clear. Blot excess water from both sides of the screen with newsprint. Dry the screen.

Step 8: TOUCHUP AND BLOCKOUT

For blocking out the screen, use **Screen Filler No. 60** or **Extra Heavy Blockout No. 10** on the dry fabric. For touchups, use **Screen Filler No. 60** or **Extra Heavy Blockout No. 10** thinned with water.

Step 9: RECLAIM THE SCREEN

Caution: Strong screen openers or ink washes may cause **EZ-FILM-30** to "lock," making reclaiming difficult. Use **All-Purpose Ink Wash** or the ink manufacturer's recommended washup solvent to remove all ink remaining in the screen. Use **Screen Degreaser Liquid No. 3** to help remove ink or solvent residues that might impair the action of the stencil remover. Rinse the screen with a powerful spray of water. Brush **Stencil Remover Liquid No. 4** or **Stencil Remover Paste No. 5** on both sides of the screen. Do not let the stencil remover dry on the screen, as this can result in a permanent stencil. Wash the screen with a strong spray of water. Use **Walk Away Haze Remover™** or **Haze Remover Paste No. 78** to remove ink and haze residues.



Technical Data Sheet

STORAGE: Unexposed screens can be stored in a dark, dry, cool environment for up to one year. Unused film can be stored in its tube for up to two years. High heat and humidity reduce shelf life.

BASE EXPOSURE TABLE for EZ-FILM-30 at 40 inches (100 cm.) on white polyester or nylon.

Light Source	EZ-FILM-30					
Carbon Arc:						
30 amps	78 sec.					
110 amps	21 sec.					
Metal Halide:						
1000 watts	52 sec.					
2000 watts	27 sec.					
3000 watts	17 sec.					
4000 watts	13 sec.					
5000 watts	11 sec.					
7000 watts	9 sec.					
Pulsed Xenon:						
2000 watts	152 sec.					
5000 watts	61 sec.					
8000 watts	38 sec.					
Mercury Vapor						
1000 watts	70 sec.					
2000 watts	33 sec.					
4000 watts	17 sec.					
Fluorescent Tubes*						
40 watts	152 sec.					

*Base Exposure Times at 4 inches (10 cm.) using unfiltered black light tubes. For "cool white" or "daylight" tubes, use at least double the exposure time.

EXPOSURE VARIABLES FACTORS: variables affecting exposure time

Mesh		Exposure Distance:		Exposure Distance:	
Dyed Mesh	1.5-2.0	20"/50 cm	0.25	56"/140 cm	1.95
		24"/60 cm	0.36	60"/150 cm	2.25
Imaging Fine line reverse printing	1.2	28"/70 cm	0.49	72"/180 cm	3.24
		32"/80 cm	0.64	84"/210 cm	4.41
		36"/90 cm	0.81	100"/250 cm	6.25
		40"/100 cm	1.00		
Adhering Direct/Indirect Method using QTX®	1.5	44"/110 cm	1.21		
		48"/120 cm	1.44		
		52"/130 cm	1.69		
Taped-up Positives					
Taped-up or montage positives, per layer	1.1				

0112dm, rev.3